(71)(72) Applicant and Inventor:

GU29 9TQ (GB).

Hampshire GU32 IQN (GB).

ON PUBLISHED UNDER THE PATENT OPERATION TREATY (PCT)

COOPER, Robin,

INTERNATIONAL APPLICATION PUBLISH	ישוח	WO 98/02197	
(51) International Patent Classification 6: A61L 33/00	A1	(11) International Publication Number: WO 98/02197 (43) International Publication Date: 22 January 1998 (22.01.98)	
(21) International Application Number: PCT/GB (22) International Filing Date: 11 July 1997 ((81) Designated States: AU, CA, GB, JP, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,		
(30) Priority Data: 9614784.8 13 July 1996 (13.07.96)		Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	

[GB/GB]: 24 Barlavington Way, Midhurst, West Sussex

(74) Agent: BROOKS, Nigel; Hill Hampton, East Meon, Petersfield,

(54) Title: THROMBORESISTANT COATING MADE OF ACRYLIC POLYMER

(57) Abstract

An acrylic polymer composition for raising the thromboresistance of a surface on which it is deposited comprising as follows (in parts by weight): Acrylic copolymer emulsion dry weight 100 parts, anti-coagulant 0-60 parts, wax emulsion dry weight 0-30 parts, water 100-700 parts.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

						••
Albania	ES	Spain	LS	Lesotho	SI	Slovenia
Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
Austria	FR	Prance	LU			Senegal
Australia	GA	Gabon	LV	•		Swaziland
Azerbaijan	GB	United Kingdom	MC	Monaco		Chad
Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova		Togo
Barbados	GH	Ghana		•		Tajikistan
Belgium	GN	Guinea		•	-	Turkmenistan
Burkina Faso	GR	Greece				Turkey
Bulgaria	HU	Hungary	ML			Trinidad and Tobago
Benin	Œ	Ireland				Ukraine
Brazil	(L	Israel		-		Uganda
Belarus	ts	Iceland				United States of America
Canada	IT	Italy				Uzbekistan
Central African Republic	JP	•				Viet Nam
Congo	KE	•		•		Yugoslavia
Switzerland	KG	•				Zimbabwe
Côte d'Ivoire	KP	- 0.		•	211	Zanosowe
Cameroon						
China	KR	-				
Cuba	KZ	Kazakatan		•		
Czech Republic	LC	Saint Lucia				
Germany						
Denmark						
Estonia	LR	Liberia	SG	Singapore		
	Armenia Austral Australia Azerbaijan Bosnia and Herzegovina Bartados Belgium Burkina Faso Bulgaria Benin Brazil Belarus Canada Central African Republic Congo Switzerland Côte d'Ivoire Cameroon China Cuba Czech Republic Germany Denmark	Armenia FI Austria FR Austria FR Australia GA Azerbaijan GB Bosnia and Herzegovina GE Barbados GH Belgium GN Burkina Faso GR Bulgaria HU Benin IE Brazil IL Belarus IS Canada IT Central African Republic JP Congo KE Switzerland KG Côte d'Ivoire KP Cameroon China KR Cuba KZ Czech Republic LC Germany LI Denmark LK	Armenia FI Finland Austria FR Prance Australia GA Gabon Azerbaijan GB United Kingdom Bosnia and Herzegovina GE Georgia Barbados GH Ghana Belgium GN Guinea Burkina Faso GR Greece Bulgaria HTU Hungary Benin IE Ireland Brazil IL Iarael Belarus IS keeland Canada IT Italy Central African Republic JP Japan Congo KE Kenya Switzerland KG Kyrgyzstan Côte d'Ivoire KP Democratic People's Cameroon China KR Republic of Korea Cuba KZ Kazakstan Czech Republic Cermany LI Liechtenstein Denmark LK Sri Lanka	Armenia FI Finland LT Austria FR Prance LU Australia GA Gabon LV Azerbaijan GB United Kingdom MC Bosnia and Herzegovina GE Georgia MD Barbados GH Ghana MG Belgium GN Guinea MK Burkina Faso GR Greece Bulgaria HU Hungary ML Benin IE Ireland MN Brazil IL Israel MR Belarus IS Iceland MW Canada IT Italy MX Central African Republic JP Japan NE Congo KE Kenya NL Switzerland KG Kyrgyzstan NO Côte d'Ivoire KP Democratic People's NZ Cameroon Republic of Korea PL Cuba KZ Kazakstan RO Czech Republic LC Saint Lucia RU Germany LI Liechtenstein SD Denmark LK Sri Lanka SE	Armenia FI Finland LT Lithuania Austria FR Prance LU Luxembourg Australia GA Gabon LV Larvia Azerbaijan GB United Kingdom MC Monaco Bosnia and Herzegovina GE Georgia MD Republic of Moldova Bartados GH Ghana MG Madagascar Belgium GN Guinea MK The former Yugoslav Burkina Faso GR Greece Republic of Macedonia Bulgaria HU Hungary ML Mali Benin IE Ireland MN Mongolia Brazil IL Israel MR Mauritania Belarus IS Iceland MW Malawi Canada IT Italy MX Mexico Central African Republic JP Japan NE Niger Congo KE Kenya NL Netherlands Switzerland KG Kyrgyzstan NO Norway Cote d'Ivoire KP Democratic People's NZ New Zealand Cameroon Republic of Korea PL Poland China KR Republic of Korea PL Portugal Cuba KZ Kazakstan RO Romania Czech Republic Germany LI Liechtenstein SD Sudan Demark LK Sri Lanka SE Sweden	Atmenia FI Finland LT Lithuania SK Austria FR Prance LU Luxembourg SN Australia GA Gabon LV Larvia SZ Azerbaijan GB United Kingdom MC Monaco TD Bosnia and Herzegovina GE Georgia MD Republic of Moldova TG Barbados GH Ghana MG Madagascar TJ Belgium GN Guinea MK The former Yugoslav TM Burkina Faso GR Greece Republic of Macedonia TR Bulgaria HU Hungary ML Mali TT Benin IE Ireland MN Mongolia UA Brazil IL Israel MR Mauritania UG Belarus IS Iceland MW Malawi US Canada IT Italy MX Mexico UZ Central African Republic JP Japan NE Niger VN Congo KE Kenya NL Netherlands YU Switzerland KG Kyrgyzstan NO Norway ZW Côte d'Ivoire KP Democratic People's NZ New Zealand Cameroon Republic FO Korea PL Poland China KR Republic of Korea PT Portugal Cuba KZ Kazakstan RO Romania Czech Republic LC Saint Lucia RU Russian Federation Germany LI Liechtenstein SD Sudan Demark LK Sri Lanka SE Sweden

The present invention relates to a method of coating a surface to render it thromboresistant.

5

Thromboresistance is important for medical devices exposed to blood flow for an extended length of time. Failure to render the surface of such a device thromboresistant can result in formation of a thrombosis, which can lodge in a life threatening position in a patient.

10

20

A number of factors can increase the thromboresistance of a surface, but no one single factor appears to ensure complete thromboresistance.

In particular, surface smoothness, with resultant deterrence for air to be retained at the surface is a significant factor. Blood coagulates in the presence of air. In addition increase in surface energy to a certain extent can improve thromboresistance.

Anti-coagulants are well known and can be deposited on a surface to improve its thromboresistance.

The object of the present invention is to provide improved thromboresistance of a surface of a medical device.

According to one aspect of my invention, there is provided a method of raising the thromboresistance of a surface of a medical device by depositing on it a non-toxic acrylic polymer composition.

According to another aspect of the invention there is provided a non-toxic acrylic polymer composition for raising the thromboresistance of a surface on which it is deposited.

WO 98/02197 PCT/GB97/01886

Preferably the composition is deposited by flowing the composition in a water based emulsion of it over the surface. Where the shape of the device lends itself, the flowing can be achieved by pumping the emulsion through it. This has particular advantage where the medical device is of complex shape, since it enables interstices which the blood can readily reach in use of the device to be treated. Alternatively, the medical device can be dipped into the emulsion. The process can be completed by blowing warm air through or over the device. This removes the water and any residual low molecular weight volatiles, from the emulsion, leaving the acrylic polymer composition deposited on the surface.

2

10

15

5

Advantageously, the acrylic polymer is provided as a copolymer.

In certain embodiments, better thromboresistance can be provided by incorporation of a water soluble anti-coagulant into the emulsion. The anti-coagulant is deposited with the acrylic polymer. It acts to discourage initiation of coagulation on the surface. Suitably the anti-coagulant can be heparin or heparin derivatives, trisodium citrate, citric acid or hirudin or hirudin derivatives.

Additionally or alternatively, a hydrophobic material can be incorporated in the emulsion. Suitably an emulsifiable wax can be used. It is deposited with the acrylic polymer and by its surface energy discourages any deposit from blood on the surface having the composition on it. Where both anti-coagulant and hydrophobic materials are incorporated, it is believed that the latter slows leaching of the former from the composition.

25

30

20

To help understanding of the invention, two specific embodiments thereof will now be described by way of example and with reference to the accompanying drawings, in which:

Figure 1 is a diagrammatic view of a blood heat exchanger being treated in a first step in depositing an acrylic copolymer composition in accordance with the invention;

Figure 2 is a similar view.of a second step in the treatment of the freat exchanger; and

Figure 3 is a similar view of other medical devices being treated in accordance with the invention.

The blood temperature regulation heat exchanger 1 shown in Figure 1 has a blood inlet 2 and a blood outlet 3. Internally, it has a highly contoured heat exchange element with an extensive surface area and small gaps between its parts. The exact structure is not shown since it is its general nature, as just described, which is relevant. However the materials of its construction, namely stainless steel, polycarbonate and potting compounds should be noted.

10

15

20

5

Figure 1 shows a pump 4 connected by pipes 5, 6 to the inlet 2 and outlet 3 of the heat exchanger via a vat 7 of emulsified thromboresistant composition described below. In a first step of treatment of the blood side of the heat exchanger, the composition is pumped through it, allowing the emulsified components of the composition to deposit over the entire internal wetted surface of the heat exchanger.

After a suitable length of time for the composition to build up, typically 20 minutes, the pump is stopped and the pipes 5, 6 removed. After the remaining liquid has drained from it, the exchanger has a drying air duct 11 connected to the inlet 2 and a blower 12 blows air through the exchanger until the composition has dried, see Figure 2. A moisture trap 13 and an exhaust extraction fan 14 are fitted to the outlet of the heat exchanger. After drying, the inlet and outlet are sealed until the device is used.

As mentioned above, the heat exchanger is made of a variety of dissimilar materials. The composition of the emulsified thromboresistant composition is as follows (in parts by weight):

Acrylic copolymer emulsion

	typically Texicryl TD 6213	100 parts
30	Anti-coagulant	
	typically trisodium citrate	0-30 parts
•	Wax emulsion	0-50 parts

WO 98/02197 PCT/GB97/01886

4

Water

0-150 parts.

Texicryl is a product from Scott Bader Co. Ltd., Wellingborough, England.

Tests have shown that this composition deposits on all the materials of the heat exchanger and renders them all thromboresistant for the periods of time for which the heat exchanger is in use, which can be up to 6 hours or so.

The composition described above includes a quantity of water of 0-150 parts by weight. However, both the polymer emulsion and the wax emulsion include water, and thus the total water content of the composition may exceed the 150 parts as stated above. Typically the polymer emulsion will contain 50% water by weight, but could contain from 20% to 80 %, and the wax emulsion will typically contain 80% water, (see later), but could contain from 30% to 90% water. Thus the composition is composed as follows (in parts by weight):

Acrylic copolymer

dry weight

100 parts

Anticoagulant

0-60 parts

Wax

20

25

30

15

10

dry weight

0-30 parts

Water

100-700 parts.

Figure 3 shows an alternative method of treatment, useful for elongate devices 21, such as stents and catheters. These are suspended from hooks 22 above a vat 23 of emulsified thromboresistant composition. The hooks are ganged together and can be lowered towards the vat, for immersion of the devices in the composition. They are successively lowered and raised until the composition has built on the surface of the devices to a sufficient extent. Where it is critical that all surfaces are completely covered including the point of connection to the hooks - as in a stent as opposed to a catheter or wound drain having an end left outside the body - the devices can be upended half way through the treatment process. As with the heat exchanger, the final step in the treatment is the drying of the composition deposited on the devices.

Stents are usually of stainless steel and can be treated with the same composition as the heat exchanger.

Wound drainage catheters are usually of polyvinylchloride PVC, polyurethane PU, or silicone material. The latter two materials are known to be more thromboresistant. Tests have shown the thromboresistance of PVC catheters can be improved to the level of those of PU catheters by treatment with a similar composition to that used for the heat exchanger, without the wax emulsion.

10

5

To improve the lubricity of the catheters, to ease their insertion and withdrawal, treatment with a further composition by overcoating with a hydrogel coating on top of the thromboresistant coating results in an equally improved thromboresistance.

15

25

The hydrogel coating can be an aqueous solution of poly(hydroxy ethyl methacrylate) (HEMA), polyvinylalcohol (PVOH), poly(N-vinyl-2-pyrrolidone) interpolymer (PVP) or poly(ethylene oxide) (PEO) as well as suitable hydrocolloids.

Texicryl TD 6213 (a Scott Bader trade name) is a styrene-acrylate copolymer emulsion. It is anticipated that other acrylic compositions will be effective, in particular copolymers based on:

(meth)acrylic esters styrene and acrylic acid esters styrene and (meth)acrylic esters.

As an alternative to Texicryl TD 6213 other suitable polymers include Revacryl 100, 123, 143, 612, all products of Harlow Chemical Co. Ltd., Harlow, England.

Texicryl TD 6213 is a copolymer emulsion, formed by emulsion polymerisation. The copolymer has a styrene butyl acrylate backbone, with a glass transition temperature of -12°C. Alternatively styrene-2-ethyl hexyl acrylate can be

5

10

20

used. The emulsion stabilising system utilises an alkali soluble copolymer with carboxylic acid functionality. This is used to achieve high resistance to water attack. Ammonia is used to solubilise the copolymer which, on drying, leaves an insoluble ammonium salt. The carboxylic acid functionality gives good compatibility (and potentially chemical bonding) with the styrene butyl acrylate, the main polymer, rendering the whole system resistant to re-emulsification.

It should be noted that not all acrylic polymers are suitable. In particular they should be non-toxic. For devices having a long life in use they should be resistant to attack by body fluids.

The wax emulsion is preferably based on either beeswax or paraffin to avoid toxicological problems. The composition of a preferred paraffin wax emulsion is as follows (in parts by weight):

15 Paraffin Wax BP

52°C solidification point

(CAS No 8002-74-2)

10-30 parts

Glycosperse TS 20

POE(20) Sorbitan tristearate ethoxylated

(CAS No 9005-71-4)

0-5 parts

Glycosperse O 20

Polysorbate 80 or

POE(20) Sorbitan monooleate ethoxylated

(CAS No 9005-65-6)

0-5 parts

25 Water

70-90 parts

Glycosperse (a trade mark of Lonza Inc., Fair Lawn, New Jersey) is an ethoxylated non-ionic surfactant.

The composition of a preferred beeswax emulsion is as follows (in parts by weight):

Yellow Beeswax BP

(melting point 61-65°C)

(CAS No 8012-89-3)

10-30 parts

Glycosperse TS 20

POE(20) Sorbitan tristearate

0-5 parts

5 Glycosperse O 20

POE(20) Sorbitan monooleate

0-5 parts

Water

70-90 parts

Advantages of the invention can include:

- 10 i) No unusual cleaning of the medical devices (beyond that dictated by their medical use) prior to treatment in accordance with the invention is thought to be necessary;
 - ii) The compositions and coating processes involved are low cost;
- iii) Use of devices treated with the coating is anticipated to result in improvements in patient safety, care and recovery rates;
 - iv) Use of an aqueous emulsion avoids the use of solvents which are expensive and/or awkward to dispose of and avoids involvement in VOC regulations.

Aside from being applicable to a wide range of substrates, the compositions of the invention are flexible, allowing their use on devices such as stents which are subject to continual flexure.

Claims:

5

PCT/GB97/01886

1. A method of raising the thromboresistance of a surface of a medical device by depositing on it a non-toxic acrylic polymer composition.

8

- 2. A method as claimed in claim 1, wherein the composition is deposited by flowing the composition in a water based emulsion of it over the surface.
- 3. A method as claimed in claim 1 or claim 2, wherein the composition is pumped through the device.
- 4. A method as claimed in claim 1 or claim 2, wherein the composition is deposited by dipping into the emulsion.
- 10 5. A method as claimed in any previous claim, wherein the process is completed by blowing warm air through or over the device to remove the water or any residual low molecular weight volatiles from the emulsion, leaving the acrylic polymer composition deposited on the surface.
- A method as claimed in any previous claim, wherein the devices treated are made
 from materials including at least one of stainless steel, polycarbonate, potting compounds, polyvinylchoride.
 - 7. A method as claimed in any previous claim, wherein anti-coagulant is deposited with the acrylic polymer.
- 8. A method as claimed in any previous claim, wherein hydrophobic material is deposited onto the surface with the acrylic polymer.
 - 9. A method as claimed in any previous claim, wherein a hydrogel is deposited over the acrylic polymer composition.
 - 10. A method as claimed in claim 9, wherein the hydrogel is an aqueous solution of poly(hydroxy ethyl methacrylate), or polyvinylalcohol, or poly(N-vinyl-2-pyrrolidone)
- 25 interpolymer, or poly(ethylene oxide) or a hydrocolloid.
 - 11. A method substantially as hereinbefore described with reference to Figures 1 and 2, or Figure 3 of the accompanying drawings.
 - 12. A composition for raising the thromboresistance of a surface on which it is deposited, the composition being a non-toxic acrylic polymer composition.
- 30 13. A composition as claimed in claim 12, wherein the acrylic polymer is provided as a copolymer.
 - 14. A composition as claimed in claim 1.2 or claim 1.3, further containing a water soluble anti-coagulant in the emulsion.

- 15. A composition as claimed in claim 14, wherein the anti-coagulant is heparin or heparin derivatives, trisodium citrate, citric acid or hirudin or hirudin derivatives.
- 16. A composition as claimed in any one of claims 12 to 15, wherein a hydrophobic material is incorporated in the emulsion.
- 5 17. A composition as claimed in claim 16, wherein the hydrophobic material is emulsifiable wax.
 - 18. A composition as claimed in claim 17, wherein the composition is as follows:-Acrylic copolymer emulsion

dry weight

100 parts

10 Anti-coagulant

0-60 parts

Wax emulsion

dry weight

0-30 parts

Water

15

30

100-700 parts

- 19. A composition as claimed in any one of claims 12 to 18, wherein the acrylic copolymer emulsion is Texicryl TD 6213 in which the copolymer has a styrene butyl acrylate backbone.
 - 20. A composition as claimed in any one of claims 12 to 18, wherein the acrylic copolymer emulsion has a styrene-2-ethyl hexyl acrylate backbone.
- 21. A composition as claimed in any one of claims 12 to 20, wherein the copolymer 20 is alkali soluble.
 - 22. A composition as claimed in any one of claims 12 to 18, wherein the acrylic copolymer emulsion is Revacryl 100, 123 143 or 612.
 - 23. A composition as claimed in any one of claims 12 to 18, wherein the acrylic composition includes copolymers based on:
- 25 (meth)acrylic esters
 styrene and acrylic acid esters
 styrene and (meth)acrylic esters.
 - 24. A composition as claimed in claim 17, or any one of claims 18 to 23 as appendant to claim 17, wherein the wax emulsion composition is as follows (in parts by weight):

Paraffin Wax BP

(52°C solidification point) (CAS No 8002-74-2)

10-30 parts

WO 98/02197 PCT/GB97/01886

10

Glycosperse TS 20

POE(20) Sorbitan tristearate ethoxylated

(CAS No 9005-71-4)

0-5 parts

Glycosperse O 20

5

Polysorbate 80 or

POE(20) Sorbitan monooleate ethoxylated

(CAS No 9005-65-6)

0-5 parts

Water

70-90 parts

25. A composition as claimed in claim 17, or any one of claims 18 to 23 as

appendant to claim 17, wherein the wax emulsion composition is as follows (in parts by weight):

Yellow Beeswax BP

(melting point 61-65°C) (CAS No 8012-89-3)

10-30 parts

Glycosperse TS 20

15

POE(20) Sorbitan tristearate

0-5 parts

Glycosperse O 20

POE(20) Sorbitan monooleate

0-5 parts

Water

70-90 parts.

26. A medical device treated in accordance with the method as claimed in any one of claims 1 to 11, with the composition as claimed in any one of claims 12 to 25.




FIGURE 1




FIGURE 2




FIGURE 3

INTERNATIONAL SEARCH REPORT

Inter onal Application No PCT/GB 97/01886

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 A61L33/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols) IPC - 6 - A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

evant to claim No
4.6.7, -15. ,26
, 20
16-18, ,23
,
16-18, ,23
•

Further documents are listed in the continuation of box C.	Patent lamily members are listed in annex.
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance. "E" earlier document but published on or after the international filling date. "L" document which may throw doubts on priority claim(s) or which is cited to establish the publicationdate of another citation or other special reason (as specified). "O" document reterring to an oral disclosure, use, exhibition or other means. "P" document published onor to the international filling date but tater than the priority date claimed.	To later document published after the international filing date or prionty date and not in conflict with the application but cited to understand the principle or theory underlying the invention. "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone. "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "\$" document member of the same patent family
Date of the actual completion of theinternational search	Date of mailing of the international search report
27 November 1997 Name and making address of the ISA	05/12/1997
•••	

11001- 0

European Patent Office, P.B. 5818 Patentiaan 2 NL - 2280 HV Ryswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo ni,

		3 10.000
C.(Continu	ation) DOCUMENTS CONSIDER O BE RELEVANT	Relevant to claim No.
ategory *	and an analysis of the relevant passages	Herevant to Class No.
X	DE 43 34 272 A (STEMBERGER AXEL DR) 13 April 1995	1-4,7, 12,14, 15,26
	see column 4, line 8 - line 27 see column 5, line 49 - line 64 see column 6, line 8 - line 16 see claims 1,4-6,9,10	
X	WO 89 07520 A (BRISTOL MYERS CO) 24 August 1989 see page 4, paragraph 2 see page 9, paragraph 2 see page 12, paragraph 1 - paragraph 6	1-6,9-12
X	see page 12, paragraph 1 paragraph 1 see claims 1,2,6,12,14 EP 0 323 341 A (TERUMO CORP) 5 July 1989 see page 7, line 22 - line 29 see claims 7.11,13-17	1-4,9-13

INTERNATIONAL SEARCH REPORT

nai Application No PCT/GB 97/01886

					PCI/GB	9//01886
Patent document cited in search repo	I	Publication date		Patent family member(s)		Publication date
EP 0484057	A	06-05-92	AU CA JP	8694091 2054847 5023391	Α	07-05-92 03-05-92 02-02-93
EP 0003389	A	08-08-79	JP	54103440	A	14-08-79
DE 4334272	A	13-04-95	DE EP	4435652 0652017		11-04-96 10-05-95
WO 8907520	Α ;	24-08-89	US AU CA EP JP	4943460 3284189 1324920 0362337 2503890	A A A	24-07-90 06-09-89 07-12-93 11-04-90 15-11-90
EP 0323341	A (JP JP JP JP JP CA DE US US	1715001 4002064 2744888 1332906 3854424 3854424 5429802 5211913	A C B A C B A A D T A	05-10-89 05-07-89 28-02-94 29-01-92 05-07-89 27-11-92 16-01-92 29-06-89 08-11-94 12-10-95 07-03-96 04-07-95 18-05-93 10-12-96

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:
☐ BLACK BORDERS
☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
☐ FADED TEXT OR DRAWING
BLURRED OR ILLEGIBLE TEXT OR DRAWING
☐ SKEWED/SLANTED IMAGES
COLOR OR BLACK AND WHITE PHOTOGRAPHS
☐ GRAY SCALE DOCUMENTS
☐ LINES OR MARKS ON ORIGINAL DOCUMENT
☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
OTHER:

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)